

EXTERIOR STUCCO



DESCRIPTION

Premier Exterior Stucco is a premixed or base and color pack system. A premium quality portland cement based color coat finish for exterior surfaces. A proprietary formulation that is factory prepared using raw ingredients that meet or exceed ASTM specifications.

COMPOSITION

Premier Exterior Stucco is a combination of portland cement, hydrated lime, graded aggregates, mineral oxide pigments, and specific additives.

MATERIAL STANDARDS

Raw materials meet or exceed the following standards:

Type S hydrated lime	ASTM C206
Portland cement Type I-II	ASTM C150
Graded aggregates for Portland cement plaster	ASTM C897-83

COLOR

Premier Exterior Stucco is prepared in any standard color from our color chart or can be custom color matched upon request.

SHELF LIFE

Six months when kept in a dry, protected area.

PREPARATION

Brown coat shall be floated and compacted over entire surface, taking care to eliminate ruptures and leaving sufficiently rough (open) to eliminate all glazed surfaces. Brown coat should be moist cured for at least 48 hours and allowed to dry completely for not less than 7 days.

Mixing

Mix in a mechanical mixer with clean potable water for at least 15 minutes to assure complete hydration. Do not attempt to re-temper a batch of material that has started to set. Under most conditions, a batch will not start to set up for 2 hours or more.

Continued on Next Page





EXTERIOR STUCCO

APPLICATION

Shall be over a base of uniform thickness and suction. Texture as per job specifications.

Premier Exterior Stucco can be either gun or hand applied:

Hand application:

Uniformly moisten the surface and allow water to dissipate before application. Apply as per desired texture. A single wall should be completed to prevent bad joints. Avoid application in damp weather or extremely hot or windy weather.

Gun application:

For best results, application should be made in two separate coats. The first coat should be thin and even completely covering the dry surface. After the first coat is dry, the second coat may be applied for desired texture and to assure uniformity of color.

COVERAGE

Coverage is affected by the method of application, conditions of surface and the desired texture. Average coverage is 10 – 15 square yards per bag.

SPECIAL NOTE

Under normal conditions, *Premier Exterior Stucco* produces uniform colors. To compensate for inclement weather, variations in the basecoat or other circumstances leading to mottled colors, specify *Premier Cement Paint* of the same color as the exterior stucco. Apply with a pressure tank sprayer after exterior stucco is thoroughly dry.

